

**IS : 525 - 1968**  
**(Reaffirmed 2001)**  
**Edition 2.1**  
**(1979-04)**

*Indian Standard*

SPECIFICATION FOR  
VARNISH, FINISHING, EXTERIOR AND  
GENERAL PURPOSES

*( First Revision )*

(Incorporating Amendment No. 1)

UDC 667.633

© BIS 2002

**BUREAU OF INDIAN STANDARDS**  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

**Price Group 3**

*Indian Standard*  
 SPECIFICATION FOR  
 VARNISH, FINISHING, EXTERIOR AND  
 GENERAL PURPOSES  
 ( *First Revision* )

Paints and Allied Products Sectional Committee, CDC 8

*Chairman*

SHRI W. E. NORRIS

*Representing*

Goodlass Nerolac Paints Private Ltd, Bombay

*Members*

SHRI H. N. RAMACHAR ( *Alternate to*  
 Shri W. E. Norris )

DR J. S. AGGARWAL Regional Research Laboratory (CSIR), Hyderabad

DR M. A. SIVASAMBAN ( *Alternate* )

DR P. K. BHANDARI Shalimar Paints Ltd, Calcutta

SHRI R. K. CHARI Indian Aluminium Co Ltd, Calcutta

SHRI A. K. CAPRIHAN ( *Alternate* )

SHRI K. K. CHOWDHURY Ministry of Defence (R & D)

SHRI I. D. SINGH ( *Alternate* )

SHRI B. K. DASGUPTA Ministry of Defence (R & D)

SHRI I. D. SINGH ( *Alternate* )

SHRI R. C. DAS GUPTA National Test House, Calcutta

SHRI S. K. BOSE ( *Alternate* )

DEPUTY DIRECTOR RESEARCH (CHEMICALS) Railway Board (Ministry of Railways)

SHRI L. R. FIALHO ( *Alternate* )

DIRECTOR OF SCIENTIFIC RESEARCH (NAVY) Naval Headquarters

SHRI K. S. GANESAN The Hyderabad Allwyn Metal Works Ltd, Hyderabad

SHRI ISHWAR SINGH ( *Alternate* )

DR JOSEPH GEORGE Central Building Research Institute (CSIR), Roorkee.

SHRI G. W. KAPSE ( *Alternate* )

SHRI T. K. S. MANI Addisons Paints and Chemicals Ltd, Madras

SHRI M. B. SATYANARAYANA ( *Alternate* )

SHRI M. N. RAO Indian Paint Association, Calcutta

SHRI B. V. DALAL ( *Alternate* )

( *Continued on page 2* )

**BUREAU OF INDIAN STANDARDS**  
 MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
 NEW DELHI 110002

## IS : 525 - 1968

( Continued from page 1 )

<i>Members</i>	<i>Representing</i>
SHRI R. K. ROKADE	The Premier Automobiles Ltd, Bombay
SHRI P. K. DESHPANDE ( <i>Alternate</i> )	
SHRI N. K. SEN	Development Commissioner, Small Scale Industries
SHRI R. R. MALHAN ( <i>Alternate</i> )	
SHRI K. N. R. SHARMA	Directorate General of Technical Development
SUPERINTENDING SURVEYOR OF WORKS (I)	Central Public Works Department, New Delhi
SURVEYOR OF WORKS (I) ( <i>Alternate</i> )	
SHRI Y. S. SWAMY	I. C. I. (India) Private Ltd, Calcutta
SHRI H. J. MISTRY ( <i>Alternate</i> )	
SHRI D. DAS GUPTA, Director (Chem)	Director General, ISI ( <i>Ex-officio Member</i> )
	<i>Secretary</i>
	SHRI M. S. SAXENA
	Deputy Director (Chem), ISI

### Finished Products Subcommittee, CDC 8 : 6

<i>Convener</i>	
SHRI T. K. S. MANI	Addisons Paints and Chemicals Ltd, Madras
	<i>Members</i>
SHRI P. K. ADHIKARI	Jenson and Nicholson (India) Ltd, Calcutta
DR J. S. AGGARWAL	Regional Research Laboratory, Hyderabad
DR M. A. SIVASAMBAN ( <i>Alternate</i> )	
SHRI N. S. BHARATIA	Indian Paint Association, Calcutta
DR P. K. BHANDARI ( <i>Alternate</i> )	
SHRI K. K. CHOWDHURY	Ministry of Defence (R & D)
SHRI B. K. DASGUPTA ( <i>Alternate</i> )	
SHRI R. C. DAS GUPTA	National Test House, Calcutta
DEPUTY DIRECTOR RESEARCH (CHEM)	Railway Board (Ministry of Railways)
SHRI V. L. MEHENDALE	Ministry of Defence (DGI)
SHRI M. N. RAO	Indian Paint Association, Calcutta
SHRI H. N. RAMAOHAR ( <i>Alternate</i> )	

### Subcommittee for Revision of Indian Standards on Finished Products, CDC 8 : 13

<i>Convener</i>	
SHRI R. C. DAS GUPTA	National Test House, Calcutta
	<i>Members</i>
SHRI P. K. ADHIKARI	Indian Paint Association, Calcutta
DEPUTY DIRECTOR RESEARCH (CHEM)	Railway Board (Ministry of Railways)
SHRI O. L. GUPTA	Ministry of Defence (DGI)
SHRI M. N. RAO	Indian Paint Association, Calcutta

*Indian Standard*  
SPECIFICATION FOR  
VARNISH, FINISHING, EXTERIOR AND  
GENERAL PURPOSES  
( *First Revision* )

0. FOREWORD

**0.1** This Indian Standard was adopted by the Indian Standards Institution on 9 January 1968, after the draft finalized by the Paints and Allied Products Sectional Committee had been approved by the Chemical Division Council.

**0.2** This standard was first issued as a tentative standard in 1954 due to non-availability of authentic technical data on durability of this material. It is now being revised on the basis of experimental data and experience gained during these years.

**0.2.1** Apart from the above, modifications in evaluating performance tests and their assessments have also been introduced through this revision. The stripping test has been elaborated by stipulating definite time intervals after which the test is to be performed. Besides, the requirements for volatile matter and viscosity have been modified to suit the material currently manufactured in the country. In the extensive and intensive study for revision, due consideration has been given for alignment of this standard with latest revised standards of this series. This revised standard, it is hoped, will go a long way in assisting the consumers and all those associated with the manufacture, use and testing of material to this standard.

**0.3** The requirements for undercoating varnish were covered in IS : 338-1952\* but the concerned technical committee responsible for preparation of this standard was of the opinion that instead of using one coat of undercoating varnish conforming to IS : 338-1952\* and another coat of finishing varnish conforming to this specification two coats of the latter may be used with improved performance and comparable cost. The Committee, therefore, decided to withdraw IS : 338-1952\* and recommended to use two coats of the material conforming to this specification in place of one coat of undercoating and another coat of finishing. IS : 338-1952\* was, therefore, withdrawn.

**0.4** This standard is one of a series of Indian Standards on varnishes ( see P 10 ).

---

\*Specification for varnish, undercoating, exterior, natural resin.

## IS : 525 - 1968

**0.5** This edition 2.1 incorporates Amendment No. 1 (April 1979). Side bar indicates modification of the text as the result of incorporation of the amendment.

**0.6** For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960\*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

### 1. SCOPE

**1.1** This standard prescribes the requirements and the methods of sampling and test for varnish, finishing, exterior and general purposes. The material is used in painting systems for protection and decoration.

### 2. TERMINOLOGY

**2.0** For the purpose of this standard, the definitions given in IS : 1303-1963† and the following shall apply.

**2.1 Registered Sample** — Sample supplied in advance by a prospective supplier and registered by the approved testing authorities after testing it to all the requirements of this standard. A complete record of its performance shall be kept in respect of all tests.

### 3. REQUIREMENTS

**3.1 Composition** — The material shall be of such a composition as to satisfy the requirements of this standard. The composition of the bulk supply shall be similar to that of the registered sample.

#### 3.2 Durability

##### 3.2.1 *Registered Sample*

**3.2.1.1** When prepared and tested for normal outdoor exposure as prescribed under **A-3**, a general breakdown of the film prepared from the sample for registration shall not occur in less than **6** months.

**3.2.1.2** A film of the material for registration shall be prepared and tested as prescribed under **A-4**, in an accelerated weathering apparatus for a period of 15 days and a complete record of its performance maintained.

NOTE — As a precaution against inadvertent accidents, the outdoor exposure test (**A-3**) and the accelerated weathering test (**A-4**) shall be carried out in duplicate.

**3.2.2 Sample from Bulk Supply** — A film of the material prepared from a representative sample from bulk supply as described in Appendix A and tested in the accelerated weathering apparatus (**A-4**)

---

\*Rules for rounding off numerical values ( *revised* ).

†Glossary of terms relating to paints ( *revised* ).

shall be not materially different in performance as compared with the record of the film of the registered sample. The film shall be examined daily for a period of 15 days.

**3.3** The material shall also comply with the requirements given in Table 1.

**TABLE 1 REQUIREMENTS FOR VARNISH, FINISHING, EXTERIOR AND GENERAL PURPOSES**

SL No.	CHARACTERISTIC	REQUIREMENT	METHOD OF TEST (REF TO CL NO. IN IS : 197-1952*)
(1)	(2)	(3)	(4)
i)	Drying time, <i>Max</i>		7.2
	a) Surface dry	8 hours	(Method I)
	b) Hard dry	18 hours	
	c) Tack free	48 hours	
ii)	Finish	Smooth and glossy	8
iii)	Colour	Not darker than a combination of 41 yellow units and 10 red units	9
iv)	Scratch hardness	No such scratch as to show the bare metal	10
v)	Flexibility and adhesion, after 96 hours air-drying	No visible damage or detachment of the film	11 (Method II)
vi)	Stripping test, after 96 hours air-drying	Scratches free from jagged edges	12
vii)	Flash point	Not below 30°C	13
viii)	Volatile matter content, percent by weight, <i>Max</i>	60.0	14
ix)	Viscosity at 30°C	1.5 to 3.0 stokes	16
x)	Acid value, <i>Max</i>	25.0	17
xi)	Keeping properties	Not less than one year from the date of manufacture	19

\*Method of test for varnishes and lacquers.

#### 4. PACKING AND MARKING

**4.1 Packing** — The material shall be packed as agreed to between the purchaser and the supplier.

**4.2 Marking** — Each container shall be marked with the following:

- a) Name, class, and type of the material;
- b) Name of the manufacturer, initials or his trade-mark, if any;
- c) Volume of the material; and
- d) Month and year of manufacture.

## IS : 525 - 1968

**4.2.1** The containers may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act, and the Rules and Regulations made thereunder. Presence of this mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard, under a well-defined system of inspection, testing and quality control during production. This system, which is devised and supervised by ISI and operated by the producer, has the further safeguard that the products as actually marketed are continuously checked by ISI for conformity to the standard. Details of conditions, under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

**4.3** Other details of packing and marking shall be in accordance with the instructions given by the purchaser.

## 5. SAMPLING

### 5.1 Preparation of Test Samples

**5.1.1** *For Registration* — The sample shall be submitted in three different containers, each containing not less than 500 ml of the material.

**5.1.1.1** As testing to the requirements of material covered by this standard involves a period of more than 6 months, the supplier is advised to submit samples for registration sufficiently in advance.

**5.1.2** *Tender Sample* — The supplier may dispense with sending a tender sample provided that he declares that the material for which the tender is given is of the same quality as the sample previously registered in his name.

**5.1.3** *Bulk Supply Sample* — Representative samples of the material shall be drawn and treated as prescribed under **3** of IS : 197-1952\*.

## 6. TEST METHODS

**6.1** Tests shall be conducted as prescribed in IS : 197-1952\* and in Appendix A. References to relevant clauses of IS : 197-1952\* are given in col 4 of Table 1 and to the Appendix in **3.2**.

**6.2** **Quality of Reagents** — Unless specified otherwise, pure chemicals and distilled water ( *see* IS : 1070-1960† ) shall be employed in tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which effect the results of analysis.

---

\*Methods of test for varnishes and lacquers. (Since revised).

†Specification for water, distilled quality ( *revised* ).

**6.3** Comparison with the performance of the registered sample shall be carried out on the basis of records maintained for the registered sample ( see **3.2.1.2** ).

## A P P E N D I X A

( Clause 3.2 )

### DETERMINATION OF DURABILITY

#### A-0. GENERAL

**A-0.1 Outline of the Method** — The durability of the varnish is determined by ascertaining actual behaviour of suitably prepared test panels in normal outdoor exposure test for a specified period and evaluating the results of this exposure by a suitable method of rating for various characteristics of the varnish film. Apart from this, the varnish is also evaluated by an accelerated weathering test wherein a prepared panel is subjected to controlled exposure of heat, light and water in an artificial weathering apparatus.

#### A-1. TEST PANELS

**A-1.1** The panels shall be of seasoned teak wood conforming to the requirements of **5.4.1** of IS : 197-1952\*. Panels for outdoor exposure shall be 300 × 150 × 25 mm in size, and for the accelerated weathering test 150 × 75 × 12 mm. The panels shall be bevelled at the edges and shall be smoothed by rubbing down with fine glass paper, the back being protected with a suitable paint.

#### A-2. PREPARATION OF TEST PANELS

**A-2.1** In the painting procedure outlined under **A-2.2**, the air-drying shall be done at the room temperature as defined under **2.8** of IS : 197-1952\* and at relative humidity of not more than 70 percent.

**A-2.2** The surface of the test panels to be exposed shall be prepared as follows:

- a) Apply one coat of liquid, transparent wood filler (conforming to IS : 345-1952†) and remove the excess after it has dried to touch, by rubbing across the grains with jute fibres or hessian cloth, and allow it to air-dry for 24 hours.

---

\*Methods of test for varnishes and lacquers. (Since revised).

†Specification for wood filler transparent, liquid.



## **IS : 525 - 1968**

- b) Rub down with emery paper No. 220/240 and wipe off the dust apply one coat of varnish, gold size (conforming to IS : 198-1952\* and allow to air-dry for 24 hours.
- c) Rub down with waterproof emery paper No. 220/240, wash and wipe off water, and when dry, apply one coat of material and allow to air-dry for 24 hours.
- d) Rub down with waterproof emery paper No. 320, wash and wipe off water, and when dry, apply one coat of the finishing varnish, and allow to air-dry for 48 hours.
- e) Rub down with waterproof emery paper No. 320, wash and wipe off water, and when dry, apply a second coat of the finishing varnish, and allow to air-dry for 7 days.

### **A-3. NORMAL OUTDOOR EXPOSURE TEST**

**A-3.0** Subject the sample for registration and the tender samples, if supplied, to normal outdoor exposure test in the manner described under **A-3.1**.

**A-3.1** Expose in the open the test panels, prepared in the manner prescribed under **A-1** and **A-2**, in duplicate, in a vertical position facing south. Commence the exposure not earlier than the last week of January and not later than the first week of March.

**A-3.1.1** Examine the condition of the exposed films at monthly intervals for gloss retention and at bimonthly intervals for other characteristics, as given below:

- a) Checking, and
- b) Blooming and spotting.

**A-3.1.2** For the above examinations, clean half the surface of the two test panels with a sponge dipped in water and wipe it dry with a piece of soft cotton cloth or chamois leather ( see IS : 1017-1964† ) prior to examination. Examine the same half of the test panels at each examination. As an aid to the examination, a magnifying glass may be used, but the evaluation shall be based on an assessment with the unaided eye. At the end of the stipulated period for durability, examine both halves of the test panels and base the evaluation for rating ( see **A-3.3** ) on the condition of the unwiped half of the test panels, which shall be wiped before the final examination.

---

\*Specification for varnish, gold size.

†Specification for chamois leather. (Since revised).

**A-3.2 Method of Rating** — The film of an unexposed test panel shall be rated with the following basic values for the respective characteristics

a) Possessing high gloss	40
b) Freedom from checking	45
c) Freedom from blooming and spotting	15
	100

NOTE — The initial rating of film may be 100 or less according to the condition of gloss and colour, the rating for freedom from checking, blooming, and spotting being always the maximum in the case of unexposed films.

**A-3.3 Evaluation of Exposed Films** — In recording the condition of exposed films at each examination, express the observed relative values of different characteristics in percentages of the basic value allotted to each characteristic under **A-3.2**. The allotment of performance value shall be multiples of 10. For arriving at an assessment, multiply the basic value for each characteristic ( see **A-3.2** ) by the percentage awarded for the performance in the test and divide the product so obtained by 100 to obtain the percentage award for the observed value of each characteristic. Take the sum total of these resulting values as the overall assessment.

**A-3.3.1** The following table is intended to serve as an example for the assessment of a varnish film after exposure:

<i>Characteristic</i>	<i>Basic Value</i>	<i>Performance Value</i>	<i>Assessment Value</i>
(1)	Percent	Percent	Percent
a) Possessing high gloss	40	100	40
b) Freedom from checking	45	50	22.5
c) Freedom from blooming and spotting	15	20	3
			65.5

**A-3.4 Results of Exposure** — Reckon the period for the general break-down of the exposed film from the date of commencement of exposure to the time when the overall assessment falls below 50 percent or when the performance value of any one characteristic, except for gloss which shall be 50 percent, falls below 25 percent of the basic value adopted for that characteristic. In the example given under **A-3.3.1**, although the overall assessment is 65.5 percent, yet the film is to be regarded as having generally broken down, because the performance value of blooming and spotting has fallen below 25 percent of its basic value.

#### **A-4. ACCELERATED WEATHERING TEST**

**A-4.1 Accelerated Weathering Apparatus** — An artificial weathering apparatus of the carbon arc type for uniform and controlled exposure to the effects of heat, light and water.

**A-4.2** Samples for registration shall be tested in duplicate in a suitable accelerated weathering apparatus ( *see A-4.1* ) and samples drawn from bulk supply shall be tested in a similar manner. The test panels shall be prepared as described under **A-2.2**. The requirements of this test shall be taken to have been satisfied if the performance of the film is not materially different as compared with the record of the film of the registered sample.

## **INDIAN STANDARDS**

### **ON**

#### **Varnishes and Enamels, Undercoating and Finishing**

IS:

- 148-1950 Ready mixed paint, brushing, undercoating, stoving, for enamels and general purposes, colour as required
- 149-1950 Ready mixed paint, spraying, undercoating, stoving, for enamels and general purposes, colour as required
- 150-1950 Ready mixed paint, brushing, finishing, stoving, enamel, colour as required
- 151-1950 Ready mixed paint, spraying, finishing, stoving, enamel, for general purpose, colour as required.
- 152-1950 Ready mixed paint, brushing, stoving, lead-free for general purposes, colour as required.
- 153- 1950 Ready mixed paint, spraying, stoving, lead-free for general purposes, colour as required
- 198-1952 Varnish, gold size
- 338-1952 Varnish, undercoating, exterior natural resin
- 339-1952 Varnish, undercoating, exterior synthetic resin
- 340-1952 Varnish, mixing
- 342-1952 Varnish, acid resisting (a) clear, and (b) tinted
- 343-1952 Varnish, paper
- 344-1952 Varnish, stoving, (a) clear, and (b) tinted
- 524-1968 Varnish, exterior, finishing, type 1 (synthetic)
- 525-1968 Varnish, exterior, finishing, type 2, general purposes
- 2932-1964 Enamel, synthetic, exterior, type 1, a) undercoating, b) finishing colour as required ( *superseding* IS : 520-1954 and IS : 521-1954 )
- 2933-1964 Enamel, exterior, type 2, a) undercoating, b) finishing, colour as required ( *superseding* IS : 522-1954 and IS : 523-1954 )

## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards : Monthly Additions'.

This Indian Standard has been developed by Technical Committee : CDC 8

### Amendments Issued Since Publication

Amend No.	Date of Issue
Amd. No. 1	April 1979

## BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002.  
Telephones: 323 01 31, 323 33 75, 323 94 02

Telegrams: Manaksanstha  
(Common to all offices)

Regional Offices:

	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 323 76 17 323 38 41
Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Kankurgachi KOLKATA 700054	{ 337 84 99, 337 85 61 337 86 26, 337 91 20
Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022	{ 60 38 43 60 20 25
Southern : C. I. T. Campus, IV Cross Road, CHENNAI 600113	{ 235 02 16, 235 04 42 235 15 19, 235 23 15
Western : Manakalaya, E9 MIDC, Marol, Andheri (East) MUMBAI 400093	{ 832 92 95, 832 78 58 832 78 91, 832 78 92
Branches : AHMEDABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. NALAGARH. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM. VISHAKHAPATNAM	